



1. Battery Pack Brief Introduction

This specification applies to the UE-36Li25BL battery manufactured by MASTER BATTERY, S.L., describes the type and size, performance, technical characteristics, warning and caution of the rechargeable cell. The battery pack support Bluetooth communication function. Through Android and IOS APP, can read the battery status and information. Especially due to the Android system's openness, different smart phone manufacturer will have their own different Bluetooth hardware version and customized feature Android systems. So the APP may not work well on some smart phones (with Android system) due to compatible issue. It is necessary for the customer to confirm whether the phone is compatible for the APP.

- **1.1 Battery Type** LiFePO4 (LFP)
- 1.2 Reference Standard GB/T 18287-2013
- **1.3 Product SPEC** 36V/25Ah 12S1P
- 1.4 Cell Brand and Model EU-2770180C-Fe-25Ah
- 1.5 Period of Warranty

24 Months from the date of shipment

1.6 Battery Specification Amendment

If the raw materials, production processing, production system or battery usage environments & other conditions need to be change, the amendment side needs provide the written advice to the other side, only the both sides come to an end, the amendment will be effective



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es







UE-36Li25BL www.masterbattery.es

2. Battery Pack Basic Features

NO.	Items		Characteristics	Testing Methods	
1	Nominal Voltage		36V	Follow (GB/T18287-2013)	
2	Nominal Capacity		25Ah	Follow (GB/T18287-2013)	
3	Minimum Capacity		23.75Ah	Follow (GB/T18287-2013)	
4	Battery Internal Impedance		Internal Impedance $\leq 100 m\Omega$	Internal Impedance Testing Machine (1kHz)	
5	Shipment Voltage		38V~42V	Multi-meter	
		Length	318mm		
6	Dimension	Width	165mm	Vernier caliper	
		Height	215mm		
7	Working	Charge	0~50°C, 45~85% RH	Temperature & Humidity Instruments	
-	Temperature	Discharge	-20~60°C, 45~85% RH		
8	Storage Temperature & Humidity Range	Short: above one month	-20~+55°C, 45~85% RH	Temperature & Humidity Instruments	
		Medium: above three months	0~+45°C, 45∼85% RH		
		Long: above one year	+5~+30°C, 45~85% RH		
9	Allowed maximum continuous charge current		25A	Multi-meter	
10	Allowed maximum continuous discharge current		25A	Multi-meter	
11	Allowed maximum reverse charge voltage		NO Allowed	1	
12	Allowed maximum charge voltage		43.8±0.2V	Multi-meter	
13	Discharge cut-off voltage		24±1V	Multi-meter	
14	Weight		About:10 Kg	Electronic scale	
15	Communication Function		Bluetooth	Though, user can read the battery system information such as voltage, current, SOC, temperature and so on.	



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es









UE-36Li25BL www.masterbattery.es

3. Battery Pack Electrical Characteristics

3.1 Testing Conditions (Unless Specially Requirements)

Temperature: 20±5°CRelated Humidity: 45~75%The testing items under the Shipment Voltage.

Atmosphere Pressure: 86~106 kPa

3.2 Battery Pack Electrical Characteristics

NO.	Items	Standards	Testing Method
1	Internal Impedance	Impedance $\leq 50 \text{m}\Omega$	Under 20±5°C Environment Temperature, the Usage Frequency of Fully Charge(1KHz), Use AC Internal Impedance test machine to test.
2	Nominal Capacity	25Ah	Rest for 0.5~1 hour after fully charge, Using electrical loader to connect with the battery output port, and discharge with constant current 0.2C till it can't discharge. Do the cycle three times, if there is one time that the discharge time is equal or more than 285 minute, you can stop.
3	Short circuit protection	No load ability after short-circuit. Comeback capability of loading after remove the lead away	Short the pack with the lead ($<50m\Omega$). If remove the lead away, connect the electronic loader with P+, P- of protection board again, so load ability comes back.
4	Allowed Maximum continuous charge Current	25A	Charging with 25A for more than 0.5h and the added temperature of battery pack less than 15°C.
5	Allowed Maximum continuous discharge Current	25A	Discharging with 25A for more than 0.5h and the added temperature of battery pack less than 15°C.
6	Over Current Protection	120A~150A	Using electron load connect with output side, discharge with 120A for about 2 sec Discharge with 150A for less than 20 millisecond.



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es









NO.	Items	Standards	Testing Meth	od		
7	The delay time of over current protection	5.0-20.0ms	Using electron load connect with output side, discharge with more than 150A and record the voltage wave of output side with oscillograph. Numerating the time of voltage from wave to zero for voltage.			ord the raph.
8	Cycle life	Discharge Capacity ≥80%	Discharge it with the current of 1C to the cut-off voltage, and store it for 15 min. Charge a battery with the current of 1C, then keep the voltage and current constant and continue to charge it until completed. After storing the battery for 15 min. The test is to be conducted as per the above cycles. The cycle should be 2500 times. At the 2001 times discharge capacity should not be less than \geq 80% with 0.2C.			
9	Discharge Temperature Characteristics	The ratio between discharge capacity and charge capacity should be not less than the following value	At 20±5°C discharge the battery with the current of 0.2C to the cut-off voltage and record charge capacity. Store the battery at the following temperature for 2h and discharge the battery with 0.2C to the cut-off voltage.			
		Discharge Current	Discharge Temperature			
			-20°C	0°C	25°C	55°C
		0.2C	60%	80%	100%	95%
10	OCharge RetentionRemain capacity ≥90%days, and then disch voltage.		en discharge	etely charge and store it for 28 charge it with 0.2C to the cut-off e the battery every three months)		
11	Over Discharge Protection furbish	Charging with 0.2C	Charge the battery with 0.2C for 5 min and measure the output voltage (\geq 38V) of the battery pack. The battery should have load.			



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es











4. Battery Pack Reliability Test

4.1 Testing condition (Unless Special Requirements)

Temperature: 20±5°C Related Humidity: 45~75% All testing under full capacity.

Atmosphere Pressure: 86~106 kPa

4.2 Reliability Test

NO.	Items	Standards	Testing Method
1	Vibration Testing	The appearance of battery should not leakage, break or explosion	Fix a charged battery on a vibrating table, vibrate it for 90 minutes in three mutually perpendicular directions at the 0.8mm resonance. The frequency is to be varied at the rate of 1 hz/min between 10 and 55 hertz.
2	High Temperature Discharge Testing	The battery should be no remarkable breakage, distortion. Discharge time should not less than 255 mins	Place a full charged battery under the environments of 55°C for 2 hours. Discharge it at the current of 0.2C to the cut-off voltage. Then keep it at 20°C \pm 5°C for 2 hours.
3	Low Temperature Discharge Testing	The battery should be no remarkable breakage, distortion. Discharge time should not less than 180 minute	Place a full charged battery under the environments of -20°C for 15-24 hours. Discharge it at the current of 0.2C to the cut-off voltage. Then keep it at 20°C \pm 5°C for 2 hours.
4	Constant Humidity & Temperature Testing	The battery should be no remarkable breakage, distortion. Discharge time should not less than 1 80 mins	Place a full charged battery under the environments of 40°C and 90%~95% RH for 48 hours. And keep it in the room temperature for 2 hours. Then discharge it at the current of 200mA to the cut-off voltage.
5	High & Low Temperature Storage	The battery should be no remarkable breakage, distortion. And charge/discharge normally	Place a full charged battery in a oven with $55\pm2^{\circ}$ C for 2 hours, then keep it under $20\pm5^{\circ}$ C for 4 hrs, then place it in a oven with $-20\pm2^{\circ}$ C for 2 hours, then keep for 4 hours under $20\pm5^{\circ}$ C, cycle as high temperature-normal temperature-low temperature-normal temperature-high temperature for 10 times.



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es











5. Battery Pack Safety Test

5.1 Testing Conditions (Unless Specially Requirements)

Temperature: 20±5°C Related Humidity: 45~75% All testing under full capacity.

Atmosphere Pressure: 86~106 kPa

5.2 Battery Pack Safety Test

NO.	Items	Standards	Testing Method
1	Short-Circuit	The battery should be no remarkable breakage, distortion. And charge normally	Use a resistor with less than 0.05Ω to make the battery short circuit for 1 hour. The appearance and characteristics are normal.
2	Over Discharge Protection Test	The battery should be no remarkable breakage, distortion. Appearance and charge are normal	Discharge the battery at the rate of 1C with the load of 30Ω for 24h. Charging for 10 sec with specified adapter, and check the voltage (\geq 32V).
3	Impact Test	The battery should be no explosion or catch fire	Place a full charged battery on a flat and put a stainless steel stick (Diamond 7.9 mm) in the middle of the battery upright. Beat the steel stick with 9.1Kg.



Polígono industrial La Dehesa C/ Dehesa Vieja, n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es








Д

6. Pack diagram





Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es














7. Packing & Transportation

7.1 Battery Packing:



7.2 Transportation

Batteries should be packed. During transportation they should be protected from vibration, shock, impact, rain and direct sunshine. The prompt vehicles are lorry, train, steamships or planes, etc.



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es









8. Battery Usage Notice

Please read and follow the handling instructions for the battery before use. Improper use of the battery may cause heat, fire, rupture, damage or capacity deterioration of the battery. MASTER BATTERY, S.L., describes is not responsible for any accidents caused by the usage without following our handling instructions.

- 8.1 Before use, please carefully read the handling instructions and the marks on the battery.
- 8.2 Please use the battery under natural, room environments. Temperature: -20~35°C , Relative Humidity: 65±20%.
- 8.3 During use, please far away from heat source, high voltage and avoid children to use. Don't beat battery.
- 8.4 Please use the special charger to charge the battery, and don't put the battery in the charger more than 24 hours.
- 8.5 Do not make the positive (+) and negative (-) terminals short circuit. And do not wet the battery , or will have dangers.
- 8.6 Please store the battery well if don't use in a long time. Please keep the battery in half charge , that is to say don't charge fully and don't discharge completely. Please avoid to touch with metal to damage the battery. Please store the battery in shade, cool and dry place.
- 8.7 Do not put the battery into a fire or water, and please safely deal with the disuse battery.



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es









9. Danger & Warning & Caution

Danger

- When Charge the battery, please use special charger and following the handling instructions.
- Only use the battery on the appointed device.
- Don't heat the battery or put into the fire.
- Don't use the battery near to fire sources and don't use or leave it in the car which temperature is over 60°C, and don't charge the battery in these environments.
- Don't throw the battery into water and don't wet it.
- Don't place the battery in the pockets and bags together with your necklace, hairpins, coins, nails or metal products. Also don't store the battery together with these products.
- Don't use metal conductors avoiding not to make the two electrodes short circuit.
- Don't reverse the two electrodes when use the battery.
- Don't penetrate the battery with sharp things
- Do not disassemble the battery.
- Don't weld the battery directly .
- Don't use the battery with seriously scratch and distortion.
- Please carefully read the handling instruction before use.

Warning

- Don't put the battery into heater, washing machine or high voltage container.
- Don't use the chargers without appointment and UL certificate.
- If the battery is not fully charged in the stated time ,please stop charging.
- Please stop using if you find the battery heat, smell odor, change color, distort or other abnormal states.
- Please far away from the battery if you find leakage or terrible smell.
- Please wash with clean water if the electrolyte leak on your skin or clothes.
- If the battery leaks, and the electrolyte get into the eyes. Do not wipe eyes, instead, rinse the eyes with clean water and immediately see a doctor.

Caution

- Place the battery far away from children in order not to swallow by them.
- Children's guardians should guide the children when they use the batter.
- Please have a profound understanding of the battery handling instruction before use.
- Please study the operating guide before Charging the battery.
- Please carefully read the operating guide of the device before put into or take out the battery from it.
- Battery has usage cycle life, if its using time is quite little than usual, please change your battery.
- If the battery cycle life is over, please take it out of the device quickly.
- If don't use the battery for a long time, please take it out of your device and store it under a low temperature & low humidity environment.
- Charge, use and store the battery should be far away from electrostatic place.
- It is strictly prohibited any series or parallel between the battery pack.



Polígono industrial La Dehesa C/ Dehesa Vieja,n°2 Nave 16 28052 Madrid (Spain) Tel. (+34) 918 021 649 Fax. (+34) 917 750 542 info@masterbattery.es





